

**PRZEDSIĘBIORSTWO USŁUGOWO REMONTOWE**  
**REMODEX**  
**ZAKŁAD BADAŃ I WDROŻEŃ PRZEMYSŁU MEBLARSKIEGO**  
Spółka z o.o.

Gruszczyn, ul. Leśna 12  
62-006 Kobylnica

e-mail: [biuro@remodex.com.pl](mailto:biuro@remodex.com.pl)  
KRS 0000099068

tel. kom. 601 391 825

SIGN: BW/PB/85/2025

DATE: 2025-05-28

Order from: 2025-03-17

## TEST REPORT

### Determination of the abrasion resistance of fabric by Martindale method

- CLIENT

STEMA P.S.A.  
ul. Towarowa 22A  
58-100 ŚWIDNICA

1. Name and type of article -

Fabric A-TM

2. Type of test

- resistance to abrasion by Martindale method

- loading – nominal pressure 12 kPa  
- translational movement along Lissajous tracks

- inspection intervals after 1000, 2000, 5000 and 10000 cycles

- the number cycles: average – **200.000**  
(after 200 000 cycles no abrasion of fabric was found, tests completed)

- resistance to pilling

(modified Martindale's method)  
- loading – 260 g,  
- translational movement along Lissajous tracks

- after 2000 cycles – degree of change 5  
**(no changes)**

- after 5000 cycles – degree of change 5  
**(no changes)**

3. This article was tested in accordance with the test procedures described in:

PN-EN ISO 12947-2:2017  
PN-EN ISO 12945-2:2021  
for conformity with PN-EN 14465:2005/A1:2007, annex A

#### TEST RESULTS:

#### POSITIVE

Article fulfill the requirements PN-EN 14465:2005/A1:2007, annex A. at the level category A

**Attention:** The test sample was acclimated according to PN-EN ISO 139:2006/A1:2012

Test operator

.....  
/M Sc. (Eng.) Piotr Błaszczak/

PREZES ZARZĄDU

.....  
mgr inż. Piotr Błaszczak

TEST REPORT contain 1 page

The test results are only valid for the article tested.

This TEST REPORT shall not be reproduced, except in full, without the written approval of the laboratory.