PRZEDSIĘBIORSTWO USŁUGOWO REMONTOWE REMODEX

ZAKŁAD BADAŃ I WDROŻEŃ PRZEMYSŁU MEBLARSKIEGO

Spółka z o.o.

Gruszczyn, ul. Leśna 12 **62-006 Kobylnica**

e-mail: biuro@remodex.com.pl KRS 0000099068 tel./fax 061 817-49-97 tel. kom. 601 391 825

SIGN: BW/JK/20/18

DATE: 2018-01-30

Order from: 2017-12-28

TEST REPORT No: 5/18/P
Assessment of ignitability

1. Sample - Fabric 1-GN - filling - standard polyurethane foam T-30.

2. CLIENT -

P.H. "STEMA" Stefan Boczyło

ul. Bystrzycka 17 58-100 ŚWIDNICA

3. Documents identifying article -

order

4. This article was tested in accordance with the test procedures described in:

PN-EN 1021-1:2014

5. Ignition source:

smouldering cigarette

6. TEST RESULTS:

POSITIVE

Test operator

/M Sc. (Eng.) Jacek Konieczny

PREZES ZARZĄDU

mar idz. Pictr Blaszczek

TEST REPORT contain 2 pages

The test results are only valid for the article tested.

This TEST REPORT shall not be reproduced, except in full, without the written approval of the laboratory.

Test report - Assessment of ignitability

Materials tested - Fabric 1-GN - filling - standard polyurethane foam T-30.

1. Ignition source: smouldering cigarette

2. Test sample conditions:

- temperature - 21 °C - relative humidity - 55 % - time - 24 h

3. Test results - NON-IGNITION

Criteria		smoul ciga	Comments							
		1	2							
Smouldering criteria	Unsafe escalating combustion	NO	NO	Test 1 – smouldering time of the cigarette 23 min. 58 s Test 2 – smouldering time of the cigarette 23 min. 46 s After these times, cigarettes burned out along the entire length. Dimensions of extent of the damage (mm)						
	Test assembly consumed	NO	NO							
	Smoulders to extremities	NO	NO							
	Smoulders through thickness	NO	NO							
	Smoulders more than 1 hour	NO	NO							
	In final examination occurrence of smoulder	NO	NO							
Flaming criteria	Occurrence of flames	NO		A CONTRACTOR OF THE PARTY OF TH				vertica		
			NO	len- gth	wi- dth	de- pth	len- gth	wi- dth	de- pth	
				69	22	21	63	20	11	

The above test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

SIGNED: LABORATORILIA

PRZEDSIĘBIORSTWO USŁUGOWO REMONTOWE REMODEX

ZAKŁAD BADAŃ I WDROŻEŃ PRZEMYSŁU MEBLARSKIEGO

Spółka z o.o.

Gruszczyn, ul. Leśna 12 **62-006 Kobylnica**

e-mail: biuro@remodex.com.pl KRS 0000099068 tel./fax 061 817-49-97 tel. kom. 601 391 825

SIGN: BW/JK/87/18

DATE: 2018-03-29

Order from: 2017-12-28

TEST REPORT No: 12/18/P
Assessment of ignitability

1. Sample - Fabric 3-GN - filling - standard polyurethane foam T-30.

2. CLIENT -

P.H. "STEMA" Stefan Boczyło

ul. Bystrzycka 17 58-100 ŚWIDNICA

3. Documents identifying article -

order

4. This article was tested in accordance with the test procedures described in:

PN-EN 1021-1:2014

5. Ignition source:

smouldering cigarette

6. TEST RESULTS:

POSITIVE

Test operator

/M Sc. (Eng.) Jacek Konieczny

PREZES ZARZĄDU

mgrinż. Piotr Blaszczak

TEST REPORT contain 2 pages

The test results are only valid for the article tested.

This TEST REPORT shall not be reproduced, except in full, without the written approval of the laboratory.

TEST REPORT No: 12/18/P

Test report - Assessment of ignitability

Materials tested - Fabric 3-GN - filling - standard polyurethane foam T-30.

1. Ignition source: smouldering cigarette

2. Test sample conditions:

- temperature

- 21 °C

- relative humidity

- 55 %

- time

- 24 h

3. Test results - NON-IGNITION

Criteria		smoul ciga	Comments							
		1	2							
Smouldering criteria	Unsafe escalating combustion	NO	NO	Test 1 – smouldering time of the cigarette 05 min. 19 s After this time, the cigarette went ou						
	Test assembly consumed	NO	NO	smoking ceased; the cigarette burned ou to 1/6 length (it did not burn out						
	Smoulders to extremities	NO	NO	completely). Test 2 – smouldering time of the cigarette 15 min. 45 s after this time, the cigarette went out, smoking ceased; the cigarette burned out 4/6 of its length. Dimensions of extent						
	Smoulders through thickness	NO	NO							
	Smoulders more than 1 hour	NO	NO							
	In final examination occurrence of smoulder	NO	NO	of the damage (mm)						
Flaming criteria	Occurrence of flames	NO		horizontal assembly			vertical assembly			
			NO	len- gth	wi- dth	de- pth	len- gth	wi- dth	de- pth	
				50	13	3	49	17	3	

The above test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

SIGNED: Mgm