

**PRZEDSIĘBIORSTWO USŁUGOWO REMONTOWE**  
**REMODEX**  
**ZAKŁAD BADAŃ I WDROŻEŃ PRZEMYSŁU MEBLARSKIEGO**  
Spółka z o.o.

Gruszczyn, ul. Leśna 12  
62-006 Kobylnica

e-mail: [biuro@remodex.com.pl](mailto:biuro@remodex.com.pl)  
KRS 0000099068

tel./fax. 61 817-49-97  
tel. kom. 601 391 825

SIGN: BW/JK/89/18

DATE: 2018-03-29

Order from: 2017-12-28


## TEST REPORT

### Determination of the abrasion resistance of fabric by Martindale method

1. *Name and type of article* - Fabric C1
2. *CLIENT* - P.H. „STEMA” Stefan Boczyło  
ul. Bystrzycka 17  
58-100 ŚWIDNICA
3. *Type of test*  
- **resistance to abrasion by Martindale method**  
- loading – nominal pressure 12 kPa  
- translational movement along Lissajous tracks  
- inspection intervals after 1000, 2000, 5000 and 10000 cycles  
- the number cycles: average – **50.000**  
- after 60000 cycles partial wipe of fibers.
4. *Documents identifying article* - order.  
This article was tested in accordance with the test procedures described in:  
PN-EN ISO 12947-2:2000  
for conformity with PN-EN 14465:2005, annex A
- TEST RESULTS:* **POSITIVE**  
**Article fulfill the requirements PN-EN 14465:2005, annex A. at the level category A**

**Attention:** The test sample was acclimated according to PN-EN 20139:1993 (ISO 139)

Test operator

  
.....  
/M Sc. (Eng.) Jacek Kenteczny

PREZES ZARZĄDU

  
mgr inż. Piotr Błaszczak

TEST REPORT contain 1 pages

The test results are only valid for the article tested. This TEST REPORT shall not be reproduced except in full, without the written approval of the laboratory.

**PRZEDSIĘBIORSTWO USŁUGOWO REMONTOWE**  
**REMODEX**  
**ZAKŁAD BADAŃ I WDROŻEŃ PRZEMYSŁU MEBLARSKIEGO**  
Spółka z o.o.

Gruszczyn, ul. Leśna 12  
62-006 Kobylnica

e-mail: [biuro@remodex.com.pl](mailto:biuro@remodex.com.pl)  
KRS 0000099068

tel./fax. 61 817-49-97  
tel. kom. 601 391 825

SIGN: BW/JK/90/18

DATE: 2018-03-29

Order from: 2017-12-28

## TEST REPORT

### Determination of the abrasion resistance of fabric by Martindale method

1. *Name and type of article -*

**Fabric TW-N2**

2. *CLIENT -*

P.H. „STEMA” Stefan Boczyło  
ul. Bystrzycka 17  
58-100 ŚWIDNICA

3. *Type of test*

- **resistance to abrasion by Martindale method**

- loading – nominal pressure 12 kPa

- translational movement along Lissajous tracks

- inspection intervals after 1000, 2000, 5000 and 10000 cycles

- the number cycles: average – **100.000**

- **no destruction point is obtained in all four samples, no damage of fabric.**

4. *Documents identifying article -*

order.

This article was tested in accordance with the test procedures described in:

**PN-EN ISO 12947-2:2000**

for conformity with PN-EN 14465:2005, annex A

*TEST RESULTS:*

**POSITIVE**

**Article fulfill the requirements PN-EN 14465:2005, annex A. at the level category A**

**Attention:** The test sample was acclimated according to PN-EN 20139:1993 (ISO 139)

Test operator



/M Sc. (Eng.) Jacek Konieczny

PREZES ZARZĄDU

  
mgr inż. Piotr Błaszczek

TEST REPORT contain 1 pages

The test results are only valid for the article tested. This TEST REPORT shall not be reproduced except in full, without the written approval of the laboratory.