

PRZEDSIĘBIORSTWO USŁUGOWO REMONTOWE
REMODEX
ZAKŁAD BADAŃ I WDROŻEŃ PRZEMYSŁU MEBLARSKIEGO
Spółka z o.o.

Gruszczyn, ul. Leśna 12
62-006 Kobylnica

e-mail: biuro@remodex.com.pl
KRS 0000099068

tel./fax 061 817-49-97
tel. kom. 601 391 825

SIGN: BW/PB/169/20

DATE: 2020-09-15

Order from: 2020-06-18

TEST REPORT No: 9/20/P
Assessment of ignitability

1. *Sample* - **Fabric GL-3 – filling – standard polyurethane foam T-30.**

2. *CLIENT* –

P.H. „STEMA” Stefan Boczyło
ul. Towarowa 22A
58-100 ŚWIDNICA

3. *Documents identifying article* –

order

4. *This article was tested in accordance with the test procedures described in:*

PN-EN 1021-1:2014


5. *Ignition source:*

smouldering cigarette


6. *TEST RESULTS:*

POSITIVE

Test operator


.....
/M Sc.(Eng.) Piotr Błaszczak/

PREZES ZARZĄDU


mgr inż. Piotr Błaszczak

TEST REPORT contain 2 pages

The test results are only valid for the article tested.

This TEST REPORT shall not be reproduced, except in full, without the written approval of the laboratory.

TEST REPORT No: 9/20/P

Test report – Assessment of ignitability

Materials tested - **Fabric GL-1 – filling – standard polyurethane foam T-30.**

1. Ignition source: smouldering cigarette

2. Test sample conditions:

- temperature - 21 °C
- relative humidity - 55 %
- time - 24 h

3. Test results – NON-IGNITION

| Criteria | | smouldering cigarette | | | Comments | | | | | |
|----------------------|---|-----------------------|----|----|--|--------|--------|-------------------|--------|--------|
| | | 1 | 2 | 3 | | | | | | |
| Smouldering criteria | Unsafe escalating combustion | NO | NO | NO | Cigarette smouldering time from 3 to 4 min. After this time, the cigarettes went out, the smoking stopped; the cigarettes burnt out about 1/5 of their length. | | | | | |
| | Test assembly consumed | NO | NO | NO | | | | | | |
| | Smoulders through thickness | NO | NO | NO | | | | | | |
| | Smoulders more than 1 hour | NO | NO | NO | Dimensions of extent of the damage (mm) | | | | | |
| | In final examination occurrence of smoulder | NO | NO | NO | | | | | | |
| Flaming criteria | Occurrence of flames | NO | NO | NO | horizontal assembly | | | vertical assembly | | |
| | | | | | len-gth | wi-dth | de-pth | len-gth | wi-dth | de-pth |
| | | | | | 14 | 8 | 2 | 13 | 9 | 1 |

The above test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

LABORATORIUM
 SIGNED: 

Order from: 2020-06-18

TEST REPORT No: 7/20/P
Assessment of ignitability

1. *Sample* - Fabric GL-1 – filling – standard polyurethane foam T-30.

2. *CLIENT* –

P.H. „STEMA” Stefan Boczyło
ul. Towarowa 22A
58-100 ŚWIDNICA

3. *Documents identifying article* –

order

4. *This article was tested in accordance with the test procedures described in:*

PN-EN 1021-1:2014


5. *Ignition source:*

smouldering cigarette

6. *TEST RESULTS:*

POSITIVE

Test operator


.....
/M Sc. (Eng.) Piotr Błaszczak/

PREZES ZARZĄDU


mgr inż. Piotr Błaszczak

TEST REPORT contain 2 pages

The test results are only valid for the article tested.

This TEST REPORT shall not be reproduced, except in full, without the written approval of the laboratory.

Test report – Assessment of ignitability

Materials tested - **Fabric GL-1 – filling – standard polyurethane foam T-30.**

1. Ignition source: **smouldering cigarette**

2. Test sample conditions:

- temperature - 21 °C
- relative humidity - 55 %
- time - 24 h

3. Test results – **NON-IGNITION**

| Criteria | | smouldering cigarette | | | Comments | | | | | |
|----------------------|---|-----------------------|----|----|---|--------|--------|-------------------|--------|--------|
| | | 1 | 2 | 3 | | | | | | |
| Smouldering criteria | Unsafe escalating combustion | NO | NO | NO | .Cigarette smouldering time from 5 to 6 min. After this time, the cigarettes went out, the smoking stopped; the cigarettes burnt out about 1/5 of their length. | | | | | |
| | Test assembly consumed | NO | NO | NO | | | | | | |
| | Smoulders through thickness | NO | NO | NO | | | | | | |
| | Smoulders more than 1 hour | NO | NO | NO | Dimensions of extent of the damage (mm) | | | | | |
| | In final examination occurrence of smoulder | NO | NO | NO | | | | | | |
| Flaming criteria | Occurrence of flames | NO | NO | NO | horizontal assembly | | | vertical assembly | | |
| | | | | | len-gth | wi-dth | de-pth | len-gth | wi-dth | de-pth |
| | | | | | 14 | 8 | 3 | 15 | 10 | 2 |

The above test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.